

**I. AMENDMENTS TO THE SPECIFICATION**

Page 3, line 7, replace "1-phenyl-3-pyrazolidinone" with --1-phenyl-3-pyrazolidinone--;

**II. AMENDMENTS TO THE CLAIMS**

The following amendments are requested according to the revised format as set forth in 1267 OG 106 (Feb. 25, 2003). Deleted matter is indicated by strike-out text and added matter is indicated by underlined text.

Claim 1 (currently amended) An electroplating solution for plating tin-copper alloy solder coatings comprising:

- a sulfonic acid electrolyte;
- a tin compound soluble in the sulfonic acid to form a tin sulfonate;
- a copper compound soluble in the sulfonic acid to form a copper sulfonate;
- a non-ionic surfactant;
- a satin brightener comprising an aromatic amine, a tertiary amine, or oxidized 1-phenyl-3-pyrazolidione; and
- an antioxidant.

Claim 7 (currently amended) The electroplating solution of claim 1 wherein the non-ionic surfactant comprises ~~polyoxyethlene~~polyoxyethylene-block-polyoxypropylene with molecular weight between 2000 and 10,000.

Claims 8-9 (canceled).